

HOMOGENEOUS  
COMPACT VINYL

# Primo Plus

| CERTIFICATION & CLASSIFICATION    | STANDARDS                                     | Primo Plus   |
|-----------------------------------|---|--|
| <b>Classification</b>             | ISO 10874                                     | Commercial: 34 Industrial: 43                                    |
| <b>Type of floor covering</b>     | ISO 10581                                     | Homogeneous vinyl flooring. Type I.                              |
| <b>ISO certification</b>          |   | Jaslo ISO 9001, Jaslo ISO 14001                                  |
| TECHNICAL CHARACTERISTICS         | STANDARDS                                     | Primo Plus   |
| <b>Total thickness</b>            | ISO 24346                                     | 2.0 mm   |
| <b>Wear layer thickness</b>       | ISO 24340                                     | 2.0 mm   |
| <b>Total weight/m<sup>2</sup></b> | ISO 23997                                     | 3060 g   |
| <b>Surface treatment</b>          |   | PUR Reinforced   |
| TECHNICAL PERFORMANCES            | STANDARDS                                     | Primo Plus   |
| <b>Residual indentation</b>       | ISO 24343-1                                   | ≤ 0.01 mm  |
| <b>Reaction to fire</b>           | EN 13501-1<br>EN ISO 9239-1<br>EN ISO 11925-2 | Class B <sub>fl</sub> s1<br>≥ 8 kW/m <sup>2</sup><br>Pass        |
| <b>Dimensional stability</b>      | ISO 23999                                     | ≤ 0.40 % for rolls<br>≤ 0.25 % for tiles                         |
| <b>Flexibility</b>                | ISO 24344, Method A                           | No cracking on 20 mm mandrel                                     |
| <b>Castor chair test</b>          | ISO 4918                                      | Suitable   |
| <b>Antistatic properties</b>      | EN 1815                                       | ≤ 2 kV   |
| <b>Light fastness</b>             | EN ISO 105-B02                                | ≥ level 6  |
| <b>Chemical resistance</b>        | ISO 26987                                     | Good resistance  |
| <b>Bacteria resistance</b>        | ISO 846: Part C                               | Does not favour growth   |
| <b>Slip resistance</b>            | DIN 51130<br>EN 13893                         | R9<br>≥ 0.3  |
| <b>Seam strength</b>              | EN 684  | Average value: ≥ 240 N/50 mm<br>Individual values: ≥ 180 N/50 mm |
| <b>Underfloor heating</b>         |   | Suitable – max 27°C  |
| <b>Form of delivery</b>           | ISO 24341 – EN 426<br>Sheet (rolls)           | 23 running meters x 200 cm                                       |
| <b>Colours</b>                    |   | 12   |

The above information is subject to modification for the benefit of further improvement (12/2016).