

ROCKY

Manufacturing process	Tufted	ISO 2424
Gauge	1/10" Loop	
Pilecomposition	100% PP	ISO 2424
Primary backing	Woven PP	ISO 2424
Secondary backing	Felt	ISO 2424
Width	400 cm ± 1%	EN 986
Pile weight	ca. 350 gr/m²	ISO 8543
Total weight	Felt ± 15% ca. 1395 gr/m²	ISO 8543
Pile height	ca. 3.7 mm	ISO 1765
Total height	Felt + 15% / -10% ca. 5.5 mm	ISO 1765
Number of knots	ca. 130.350 /m² + 10% / -7,5%	ISO 1763
Fire classification	Felt Efl (EN13501-1)	EN 13501-1
Light fastness	≥ 5	105-B02
Wearability	≥ 4	105-X12
Water fastness	≥ 4	105-E01
Thermal resistance	0.12 m² K/W	ISO 8302
Sound insulation	10 dB	ISO 10140

Floorsymbols Vlies



Certificates

